

Corden EPS Evolution Tank – Gas and Hydrocarbon Barrier is a multilayer, polyethylene membrane with an adhesive coating for vertical application; specifically designed and manufactured to perform as a Methane, Carbon Dioxide, Radon, Ground Gas, VOC, air & Moisture, and Hydrocarbon protection system.

Corden EPS Evolution Tank complies with the latest codes of practice as published by BRE, CIRIA (C748) and BSI (BS 8485:2015 and BS8102:2009). Suitable for use as Ground Gas/Hydrocarbon protection for NHBC **GREEN**, **AMBER 1**, **AMBER 2**, and **RED** site.

DESCRIPTION

Corden EPS Evolution Tank is a self-adhesive tanking membrane comprised of **Corden EPS Evolution VOC** and a specialist all weather adhesive backing.

The product is available in roll format, 1.0m x 20m and as detailing strip at 0.3m x 20m (other dimensions available on request) in Black and Silver colour.

Corden EPS Evolution Tank Hydrocarbon Barrier offers a safe solution for the protection of buildings and occupiers against all levels of hydrocarbons, methane, carbon dioxide and radon ingress. Typically, these are sites previously used as petrol stations, coalfields, landfill sites, contaminated industrial sites, Fracking sites, and heavily contaminated sites. The membrane also acts as a dampproof membrane. **Corden EPS Evolution Tank** is designed to withstand the most aggressive environments. Testing has been completed in accordance with BS8485:2015 and C748 to determine the permeation rates for Methane, Carbon Dioxide, and a range of VOC's.

Immersion testing has also been completed to for Chemical Resistance to EN 14414 and EN 14415.

Durability and Chemical Resistance			
Chemical Resistance - SULFURIC ACID (10% solution of Sulfuric Acid (H2SO4)) 50° for 56 days	EN 14414 - A	Tensile strength Retained	100%
		Result	PASS
Chemical Resistance - BASIC (Calcium Hydroxide saturated suspension) 50° for 56 days	EN 14414 - B	Tensile strength Retained	100%
		Result	PASS
Chemical Resistance - SOLVENTS (35% Diesel, 35% Paraffin, 30% Oil HD30 (vol) 50° for 56 days	EN 14414 - C	Tensile strength Retained	100%
		Result	PASS
Chemical Resistance - SYNTHETIC LEACHATE (Mixture of 14 acids, chlorides, sulphates and phosphate) 50° for 56 days	EN 14414 - D	Tensile strength Retained	100%
		Result	PASS
Resistance to Leaching - HOT WATER (Deionised water) 50° for 56 days.	EN 14415 - A	Tensile strength Retained	100%
		Result	PASS
Resistance to Leaching - AQUEOUS ALKALINE (Saturated Calcium Hydroxide) 50° for 56 days.	EN 14415 - B	Tensile strength Retained	100%
		Result	PASS
Resistance to Leaching - ORGANIC ALCOHOL (30% methanol, 30% isopropanol, 40% glycol) 50° for 56 days	EN 14415 - C	Tensile strength Retained	100%
		Result	PASS

**Values are Typical, with the exception of Thickness, which is Nominal. Typical indicates the mean value derived from the samples taken for any one test as defined in the BS EN ISO standard - usually the mean of five samples. Nominal is a guide value.*

(OTHER ROLL SIZES ARE AVAILABLE ON REQUEST)

Corden EPS Evolution Tank			
Characteristic	Test Method	Unit	Corden EPS Evolution Tank
Physical Properties			
Thickness	EN 1849-2	mm	1.2
Width	EN 1849-2	M	1 or 0.3
Length	EN 1849-2	M	20
Weight	EN 1849-2	g/m ²	1000
Hydraulic Properties			
Water Vapour Transmission Rate	EN 1931	g/m ² /day	0.14
Water tightness (60kPa)	EN 1928	-	PASS
Water tightness (196kPa-20m water head) [Basement application]	EN 1928	-	PASS
Mechanical Properties			
Resistance to Static Load	EN 12730	Kg	>20
Tensile Strength (MD)	EN 12311 -1	N/50mm	>550
Tensile Strength (CMD)	EN 12311 -1	N/50mm	>400
Tear Resistance (MD)	EN 12310 -1	N	>300
Tear Resistance (CMD)	EN 12310 -1	N	>300
Resistance to Impact	EN 12691 - B	N	650
Reaction to Fire	EN ISO 11925-2	Class	E
Resistance to Artificial Ageing	EN 1296	-	PASS
Resistance to Chemicals	EN 1847	-	PASS
Vapour Permeability - 100% concentration			
Transmission rate of Benzene	EN ISO 15105 - 2	mg/m ² /day	2250
Transmission rate of Toluene	EN ISO 15105 - 2	mg/m ² /day	2370
Transmission rate of Ethyl Benzene	EN ISO 15105 - 2	mg/m ² /day	400
Transmission rate of Xylene (m,p,o)	EN ISO 15105 - 2	mg/m ² /day	690
Transmission rate of Hexane	EN ISO 15105 - 2	mg/m ² /day	95.25
Transmission rate of Vinyl Chloride	EN ISO 15105 - 2	mg/m ² /day	36.44
Transmission rate of Trichloroethene	EN ISO 15105 - 2	mg/m ² /day	1.44
Transmission rate of Tetrachloroethene	EN ISO 15105 - 2	mg/m ² /day	1.59
Gas Permeability			
Methane Permeability (WELDED JOINT)	EN ISO 15105 - 1	ml/m ² /day/atm	1.00
Methane Permeability	EN ISO 15105 - 1	ml/m ² /day/atm	0.13
Carbon Dioxide Permeability	EN ISO 15105 - 1	ml/m ² /day/atm	3.01
Radon Permeability	SP Method 3873	m ² /s	3.0 x 10 ⁻⁹
Compliance and Certification			
CE Mark - EN13967			
NHBC Standards Compliant			
BS 8485:2015 Compliant			
CIRIA C748 Compliant			
BS 8102:2009 Compliant [TYPE A Waterproofing Barrier]			

HANDLING

Roll weights can be in excess of 20kg and hence appropriate care and equipment is required for unloading and handling. This product is non-toxic nor flammable.

STORAGE

Rolls of **Corden EPS Evolution Tank** should be stored horizontally, and pallets should not be stacked on top of one another. **Corden EPS Evolution Tank** should be stored in a cool, dry place, and be protected from exposure to rain, sun, heat and cold temperatures prior to installation.

INSTALLATION

Corden EPS Evolution Tank should be installed in accordance with the product installation guidelines, and in accordance with BS 8485:2015.

ADDITIONAL INFORMATION

For additional information or assistance, please contact JUTA UK directly.

ACCESSORY PRODUCTS

A wide range of accessories are available for use with the **Corden EPS Evolution Tank**

ADDITIONAL INFORMATION

For additional information or assistance, please contact **Corden EPS** directly.